

PA66 GF25-FR

25%玻璃纤维增强, 高强度, 高耐温性, 良好的尺寸稳定性, 阻燃级。

25%Glass fiber reinforced,high strength,high heat resistance,good dimensional stability,flame resistant.

性能 Properties	测试标准 Test Standards	测试条件 Test Conditions	单位 Units	典型值 Typical Values
物理性能 Physical				
密度 Density	D792	23℃	g/cm ³	1.52
灰份含量 Ash Content	D2584	—	%	25
收缩率 Mold Shrinkage	D955	23℃,flow	%	0.3
	D955	23℃,xflow	%	0.5
吸湿率 Moisture Absorption	D570	23℃/24h.	%	1.1
阻燃性 Flammability	UL94	1.5mm	—	V-0
机械性能 Mechanical				
拉伸强度 Tensile Strength	D638	10mm/min	Mpa	100
伸长率 Elongation at break	D638	10mm/min	%	3
弯曲强度 Flexural Strength	D790	1.3mm/min	Mpa	150
弯曲模量 Flexural Modulus	D790	1.3mm/min	Mpa	7000
冲击强度Impact Strength,IZOD Unnotched	D256	23℃	kJ/m ²	—
缺口冲击强度Impact Strength,IZOD Notched	D256	23℃	kJ/m ²	6.5
缺口冲击强度Impact Strength,IZOD Notched	D256	-20℃	kJ/m ²	—
热性能 Thermal				
热变形温度Heat Deflection Temperature	D648	1.80Mpa	℃	250
热变形温度Heat Deflection Temperature	D648	0.45Mpa	℃	—
电性能 Electrical				
表面电阻率 Siface Resistivity	D257	23℃	Ω	10 ¹³
体积电阻率 Volume Resistivity	D257	23℃	Ω.cm	—
介电强度 Dielectric Strength	D149	2mm,in oil	Kv/mm	17

1)染色料的性能可能与以上数值有不同。所有数据是在 23℃、50%相对湿度的环境中存放48小时后测试所得。除流动指数外的其它性能使用注塑样条测试。

Variations within normal tolerances are possible for various colors. All values are measured at least after 48 hours storage at 23° C/50% relative humidity. All properties, except the melt flow rates, are measured on injection molded samples.

2)典型值是指实验平均数据, 仅用于使用时的参考, 不作为产品的标准。

Only typical data for selection purposes.Property values is the average experimental data, when used only for reference, not as a product standards.

PA66 GF25-FR

加工条件 Processing Conditions

项目 Item	工艺范围 Range
熔体温度 Melt Temp.	260-295℃
料筒温度 Front - Zone 3 Temperature	265-295℃
料筒温度 Middle - Zone 2 Temperature	270-285℃
料筒温度 Rear - Zone 1 Temperature	240-265℃
模具温度 Mold Temp.	40-90℃
注塑速度 Injection Speed	Moderate to high
背压 Back Pressure	0.1-0.2Mpa
预干燥 Pre-Drying Temperature	90-100℃
预干燥 Pre-Drying time	4-6hr
最大含湿量 Maximum Moisture Content	0.03%

以上数值为实验室测得，实际可能会有所不同，可根据不同机型、不同模具以及产品要求，做适当调整。

Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

标准免责声明

您根据您需求, 使用我们的产品和相关信息(无论是口头、书面或通过生产评估), 包括任何建议配比和工艺, 是我们无法控制的。因此, 重要的是您测试我们的产品、分析信息来决定是否适合你的预期用途和应用。从技术以及健康、安全和环保角度来看, 必须通过测试来确定适宜性。所有的信息和技术支持是不做保证或担保。

Standard Disclaimer

Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed Seller. No statement Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

燃烧性能

燃烧性能的结果是小规模的实验室检测的情况, 不能反映灾害或任何其他材料在实际火灾条件。

Flammability

Flammability results are based on small-scale laboratory tests for purposes of relative comparison and are not intended to reflect the hazards presented by this or any other material under actual fire conditions.

安全防护

使用这些产品之前, 你必须阅读和熟悉安全与防护方面的信息, 了解他们的危害及正确使用和处理。相关信息有, 材料安全数据表(MSDS)和产品标签。

Health and Safety

Before working with these products, you must read and become familiar with the safety and protection of information on their hazards, proper use, and handling. Relevant information is material safety data sheets (MSDS) and product labels.